

# AquaSolve™ Hypromellose Acetate Succinate (HPMCAS)

## Versatile Pharmaceutical Polymers for Improved Solubility




AquaSolve (AquaSolve AS™ in the United Kingdom) HPMCAS is a mixture of acetic acid and monosuccinic acid esters of hydroxypropylmethylcellulose. AquaSolve HPMCAS is used as a solid dispersion polymer for bioavailability enhancement of poorly soluble active pharmaceutical ingredients (APIs). The versatility of this polymer in addressing solubility issues is a result of its unique properties. These properties lead to enhanced absorption when HPMCAS-based solid dispersions are dosed orally.

### Features and Benefits of AquaSolve HPMCAS

| Feature  | Benefit   |
|--|---|
| Several substitution ranges                                  | Scope for API-dependent formulation flexibility   |
| Low solution viscosity in multiple organic solvents          | Economical and controllable spray-dried dispersion processes  |
| High $T_g$   | Excellent physical stability due to low drug mobility   |
| Performance matches monograph-compliant competitive products | Reduced risk in excipient sourcing and ease of interchangeability   |
| HPMCAS is amphiphilic  | Insoluble drug molecules interact with the hydrophobic regions; hydrophilic regions allow the formation of colloids in aqueous solution |
| Enteric polymer, so partially ionized above pH 5             | Charge on the polymer minimizes the formation of large agglomerates, thus stabilizing drug-polymer colloids                             |

AquaSolve HPMCAS is also used as an enteric coating polymer and in preparation of sustained drug-release formulations; the release rate of the API from the matrix is pH dependent.



AquaSolve HPMCAS is available in three grades differentiated by degree/ratio of substitution. Each grade is available in two particle sizes. Consult the product data sheet or the excipient information package for further details on specifications. Additional substitution levels and ranges are available upon request. Detailed product information is available in the *AquaSolve™ and AquaSolve AS™ Hydroxypropylmethylcellulose Acetate Succinate Physical and Chemical Properties Handbook*.

AquaSolve HPMCAS complies with National Formulary and Japanese Pharmaceutical Excipients specifications (shaded box)


**ASHLAND**

With good chemistry great things happen.™


## Improved Solubility Can Be Polymer Dependent

Improved solubility and bioavailability of an API is dependent upon which grade of polymer is selected as well as upon the API. The properties of three APIs we have worked with are shown in the table.

| Property            | Itraconazole     | Ezetimibe     | Felodipine |
|---------------------|------------------|---------------|------------|
| T <sub>m</sub> (°C) | 166.2            | 163           | 141.6      |
| T <sub>g</sub> (°C) | 59               | 70            | 43         |
| LogP                | 5.66             | 4.5           | 4.83       |
| pKa1                | 3.70 (weak base) | 9 (weak acid) | Neutral    |
| Solubility (mg/l)   | <1               | 8             | 19.7       |




The H grade of AquaSolve HPMCAS dissolves at a higher pH than the L and M grades and so it takes longer to release in gastric fluid.




Itraconazole is a weak base and lipophilic, hence a more hydrophilic grade of HPMCAS (indicated by a higher succinoyl ratio) is required for rapid dissolution.

## Improved Solubility Can Be API Dependent



Differences in solubility across APIs can be observed when using the same grade of HPMCAS with different APIs as can be seen in the variation in solubility for solid dispersions of ezetimibe, felodipine and itraconazole made with M grades of AquaSolve HPMCAS. The release profiles of the three APIs vary widely with the same (M) grade of HPMCAS.

## Delayed Recrystallization



There have been a number of reports demonstrating superior performance of HPMCAS over existing polymers in terms of solubilizing efficacy in vivo and recrystallization inhibition during storage. Some HPMCAS solid dispersions exhibit characteristic spring-and-parachute shape dissolution curves, whereby a large percentage of API can be released quickly and supersaturation can be maintained for prolonged time periods. Each grade of AquaSolve HPMCAS maintains a high concentration of felodipine in solution over time, but the M and H grade curves demonstrate this prolonged supersaturation particularly well.

## Global Headquarters

Ashland Inc.  
50 East RiverCenter Blvd.  
P.O. Box 391  
Covington, KY 41012-0391 U.S.A.  
Tel: +1 859 815 3333

Ashland Specialty Ingredients  
8145 Blazer Drive  
Wilmington, DE 19808 U.S.A.  
Tel: +1 877 546 2782

## Regional Centers

Europe — Switzerland  
Tel: +41 52 560 55 00  
Fax: +41 52 560 55 99

India — Maharashtra  
Tel: +91 22 61489696  
Fax: +91 22 61712514

Asia Pacific — Singapore  
Tel.: +65 6775 5366  
Fax: +65 6776 9690

Latin America — Mexico  
Tel.: +5255 5211 0111  
Fax: +5255 5212 0883

[pharmaceutical@ashland.com](mailto:pharmaceutical@ashland.com)

[ashland.com/pharmaceutical](http://ashland.com/pharmaceutical)

\* Registered trademark, Ashland or its subsidiaries, registered in various countries  
™ Trademark, Ashland or its subsidiaries, registered in various countries  
© 2013, Ashland  
PC12474

All statements, information and data presented herein are believed to be accurate and reliable, but are not to be taken as a guarantee, an express warranty, or an implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which Ashland Inc. and its subsidiaries assume legal responsibility.

# ASHLAND®